

Prime Flex

POLY- 3350 / ISO-1003

HANDLING: Vacuum Mold Shoe sole PU system

	MATERIAL A	MATERIAL B	
	POLY-3350	ISO-1003	
<i>Parameter</i>	<i>Value</i>	<i>Value</i>	<i>Unit</i>
Apperance at room temperature	White milky	Yellow transparent	-
Melting point	-10°C	0°C	°C
Solid material melting time	0-1	0-1	hours
Viscosity at 35 °C	1500	400	mPa·s
Density at working temperature	1.1	1.05	g/cm³
Mixing ratio	100	65-70	V/m
Working temperature	45	40	°C
Moulds temperature		45-55	°C
Demoulding time		180-240	second
Reaction performance (Cream Time/Thread Time)		7-9	second
Free Density		0.14-0.21	g/cm³

MECHANICAL PERFORMANCE OF THE FOAM

<i>Parameter</i>	<i>Value</i>	<i>Unit</i>
Density(UNI 10902)	0.27-0.3	g/cm³
Hardness (UNI EN ISO 868)	50-55	Shore C
Elogation at break(UNI EN 12803)	300	%
Tensile strength at break (UNI 12803)	7	MPa
Tear Resistance(UNI EN 12771)	30	N/mm
Abrasion resistance (UNI EN 12770)	200	mg
Flexural fatigue resistance(UNI EN ISO 17707)	100000	Flex time
Test temperature:+23°C without original hole		

*It is based on test results from samples taken on 10mm plates using Derkim Polyurethane test methods in our laboratories.

*It is recommended that our products be stored at room temperature in places that are not exposed to direct sunlight and rain.